

**TEGOLA CANADESE S.p.A.**

Via dell'industria 21, 31029 Vittorio Veneto (TV) ITALY

Tel. +39-0438-9111 Fax +39-0438-911-260

www.tegolacanadese.com e-mail: office@tegolacanadese.com



### **Technical Data Sheet**

## **FIMIZOL EXPRESS**

*Primer based on bitumen and organic solvent  
standard SRPS U.M3.240*

FIMIZOL EXPRESS is a homogeneous mixture of bitumen and a special organic solvent which ensures short drying period thus fulfilling requirements of modern construction industry.

<b>Characteristics</b>	<b>Unit</b>	<b>Value</b>
<i>Bitumen content</i>	%	min. 30
<i>Softening point acc. to R&amp;B</i>	°C	min. 55
<i>Point of inflammability acc. to Markuson</i>	°C	min. 35
<i>Flow resistance at elevated temperature, no leakage</i>	°C	70
<i>Flexibility at low temperature, no cracking</i>	°C	4
<i>Drying period</i>	h	1

### **USAGE**

FIMIZOL EXPRESS is applied as previous primer for preparation of waterproofing substrate, dust removal etc. It is used in cold condition, without dilution, well mixed beforehand. It should be put with brush, roller or machine. The next work phase is done after drying of the painted mass. It must not be heated. Usage of open flame during work is PPOHIBITED. When applied in closed areas good airing must be ensured. The average consumption is 0,35 kg/m<sup>2</sup>, and varies from 0,2-0,5 kg/m<sup>2</sup>.

### **DELIVERY, TRANSPORTATION AND STORAGE**

FIMIZOL EXPRESS is delivered in packaging of 4,5; 9; 23 and 180 kg. As highly inflammable material it is stored and transported in covered areas and vehicles, protected from the sun, heat and mechanical damages.

**TEGOLA CANADESE S.p.A.**

Via dell'industria 21, 31029 Vittorio Veneto (TV) ITALY

Tel. +39-0438-9111 Fax +39-0438-911-260

www.tegolacanadese.com e-mail: office@tegolacanadese.com



## MŰSZAKI ADATLAP

# FIMIZOL EXPRESS

Szerves oldószeres bitumenes alapozó  
szabvány: SRPS U.M3.240

A FIMIZOL EXPRESS egy homogén bitumenmassza, mely bitumenből és szerves oldószerből áll. Ennek köszönhető rövid száradási ideje, igazodva a modern építőipari igényekhez.

Műszaki jellemzők	Egység	Érték
Bitumen tartalom	%	min. 30
Lágyuláspont, R&B szerint	°C	min. 55
gyulladáspont "Markson" szerint	°C	min. 35
kúszási ellenállás magas hőmérsékleten, megfolyás nélkül	°C	70
hideghajlíthatóság, repedésmentesen	°C	4
Száradási idő	h	1

## FELHASZNÁLÁS

A FIMIZOL EXPRESS egy előkészítő, alapozó termék vízszigetelések készítéséhez. A terméket hideg állapotában kell alkalmazni, hígítás nélkül, jól felkeverve. Felhordása történhet ecseteléssel, rollerrel vagy egyéb géppel. A következő munkafázis előtt az alapozó rétegnek meg kell száradnia. Száradást tilos hőközléssel gyorsítani. Alapozási munkavégzés alatt nyílt láng használata TILOS! Zárt térben való használat esetén jó átszellőztetést kell biztosítani. Az átlagos anyagszükséglet  $0,35 \text{ kg/m}^2$ , ettől való eltérés:  $0,2-0,5 \text{ kg/m}^2$ .

## SZÁLLÍTÁS ÉS TÁROLÁS

FIMIZOL EXPRESS-t 4,5; 9; 23és 180 kg-os kiszerelésben szállítják. Mivel a termék kifejezetten gyúlékony, tárolása és szállítása zárt térben, gumikerekeken történhet, napsugárzástól, felmelegedéstől és mechanikai sérülésektől védve.