

BARRIER TPO TNT 1.5 I

TPO Flexible waterproofing sheet, polyester reinforced with PP TNT

MEMBRANE

Raw material			TPO	
visible defects	EN 1850-2		pass	
length	EN 1848-2	m	30,5	+/- 1%
width	EN 1848-2	m	3,05	+/- 5%
straightness	EN 1848-2	mm	<15	
flatness	EN 1848-2	mm	<25	
effective thickness	EN 1928	mm	1,4	+/- 5%
watertightness	EN 1928		Pass	(60kpa/24h)
tensile properties m/c	EN 12311-2	N/50mm	>1500	
elongation	EN 12311-2	%	>30	
dimensional stability	EN 1107-2	%	-0,35	
resistance to impact	EN 12691-2	mm	npd	
foldability at low temperature	EN 495-5	°C	npd	
joint strength peel resistance	EN 12316-2	N/50mm	>400	
joint strength tensile shear resistance	EN 12317-2	N/50mm	>1100	
resistance to tearing md	EN 12310-2	N	>600	
resistance to tearing cmd	EN 12310-2	N	>800	

OTHER INFO

fire properties	EN 13501-1	CLASSE	E	
fire properties	EN 13501-5	CLASSE	B roof (t1)	
UV resistance	EN 1297		npd	

The information given in this data sheet is to the best of our knowledge true and correct, however new research results and practical experience can make revisions necessary. No guarantee or liability can be drawn from the information mentioned herein.



TeMa Technologies and Materials srl
Via dell'Industria, 21 31029 Vittorio V.to (TV) - I -
Tel. +39.0438.50.31 - Fax +39.0438.50.34.60
e-mail: info@temacorporation.com
www.temacorporation.com

rev.1 nov-08